



**SHALIMAR
PAINTS**

TUFFKOTE

PROTECTIVE COATINGS

EPIGARD FINISH

Data Sheet No. SPL/PMG/2019100013

A high performance, two-component amine cured epoxy glossy enamel specially formulated by using selected chemical resistant pigments. It forms the finish coat in heavy duty coating systems for metal at medium corrosive environment. The coating remains unaffected by many corrosive chemicals and solvents and renders durable finish in industrial atmosphere.

Product Information

Color	Selected Range
Finish	Satin to Semi glossy
Flash Point	Above 23°C
Mixing Ratio (By Volume)	Base : Accelerator 3 : 1
Volume Solids	42 ± 2 %
Recommended dry film thickness	35 – 50 microns
Corresponding wet film thickness	83 - 120 microns
Theoretical Spreading Rate	12 .0 - 8.40 Sq.m/ltr
Drying time @ 30°C	Surface dry 2 - 4 hours Handle dry 8 hours Full cure 7 days
Interval before Over-coating	Minimum 18 hours Maximum 7 days For optimum inter coat adhesion overcoat within 48 hours
Volatile organic Compound (VOC)	490 gm/ltr (EPA Method 24)
Storage Life	12 months minimum @ 30°C if stored in a dry sealed container at shaded condition away from heat source and ignition
Dry Heat Resistance	Up to 150°C (Intermittent)

Uses

In heavy duty coating systems for Pulp & Paper mills, Chemical Plants, Gas Plants, Oil Refineries, Power Plants, Fertilizer Plants, Sugar Mills, Food & Pharmaceutical units, Mining & Machinery Units at medium corrosive environment

Surface Preparation

Steel Surface

Surface to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

It is always recommended to apply suitable primer coat before application of this product. Ensure surfaces to be coated is dried and followed overcoating interval and if required sufficiently roughened by emery paper.

This product can be applied over Hand & Power tool cleaning to St2 & St3.

For damage area rectification contact the Technical team of Shalimar Paints limited

Application Details

Method of Application

Brush / Roller / Spray

Notes on Airless Spray

Tip Range	15 – 21 thou.
Total Output	1900 – 2800 psi.
Fluid Pressure	(147- 196 kg/sq.cm
Pot Life	6 - 8 hours
Thinner	Thinner 6756

Notes on Air Spray

Nozzle Orifice – 1.2 mm to 3 mm
Nozzle Pressure – 0.3-0.4 Mpa

Limitations

The finish tends to chalk when exposed to sunlight although protective properties of the film remain practically unaffected.

Typical System Selection Guide

SURFACE	1 ST COAT	2 ND COAT	3 RD COAT	4 TH COAT
Steel	Epigard Zinc Rich / Epigard Zinc Phosphate Primer	Epigard HB MIO	Epigard Finish	Epigard Finish
- Do -	Epiplus 56	Epigard Finish	Epigard Finish	-

Chemical Resistance Guide (with suitable top coat)

EXPOSURE	Acids	Alkalis	Solvents	Salt	Water
SPLASH & SPILLAGE	Good	Excellent	Good	Excellent	Excellent
FUMES & OUTDOOR EXPOSURE	Good	Excellent	Very Good	Excellent	Excellent

Health & Safety

Use Proper Personal Protective Equipment(PPE) during application of this product.

Please consult Material Safety Datasheet (MSDS)

Precaution

Provide adequate ventilation during application and drying. Clean Spray gun equipment and hose immediately after application of material.

Standard Pack Size

20 litres - For available pack size contact local representative of Shalimar Paints Limited

NOTES:

1. This Product datasheet supersedes all previous datasheet and subject to change without prior notice
2. Do not apply when surface temperature is less than 3 °C than dew point.
3. Mixing with mechanical agitator is strongly recommended
4. Use material within stipulated pot life
5. Do not apply paints when environment temperature rises above 50 °C or when relative humidity rises above 85%. Do not apply during rain, fog or mist.
6. Use of thinners other than supplied or approved by Shalimar may adversely affect product performance
7. Drying is dependent on temperature, relative humidity and thickness; ranges is given for considering those parameters
8. System Guide is a typical and for indicative purpose only, however this can have wide range of combination. For details, please contact Shalimar Paints limited
9. Request for details information of surface preparation, paint application on the recommended coating system

DISCLAIMER: This PDS is by no means a comprehensive data. The company will not be liable for losses or damages howsoever caused including liability for negligence, which may be suffered by the user of the data contained therein. It is the user's responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of result is extended since conditions of use are beyond our control. Liability is limited to replacement of the product hence cost of labour charges or consequential damages are excluded.