



**SHALIMAR
PAINTS**

TUFFKOTE

PROTECTIVE COATINGS

EPIGARD MIO INTERMEDIATE

Data Sheet No. SPL/PMG/2019100076

A two pack polyamide cured high solid epoxy coating based on laminar micaceous iron oxide pigment. Designed for application on structural steel as an intermediate coat exposed to industrial environment. The product acts as a tough abrasion resistant barrier coat with excellent impermeability to moisture. The grey version contains Titanium dioxide pigment apart from MIO pigment.

Product Information

Color	Brown/ Grey
Finish	Eggshell
Flash Point	Above 23°C
Mixing Ratio (By Volume)	Base : Accelerator 9 : 1
Volume Solids	60 ± 3 %
Recommended dry film thickness	75 - 100 microns
Corresponding wet film thickness	125 – 175 microns
Theoretical Spreading Rate	8.0 – 6.0 Sq.m/ltr
Drying time @ 30°C & RH -50	Surface dry 45 Minutes Handle dry 1 – 2 Hours Hard dry 8-12 Hours Full curing 7 days
Interval before Over-coating @ 30°C & RH -50	Minimum 18 hours Maximum Indefinite
Volatile Organic Compound (VOC)	350 gm/ltr (EPA Method 24)
Storage Life	12 months minimum @30°C if stored in a dry sealed container at shaded condition away from heat source and ignition.
Dry Heat Resistance	Up to 120°C (Intermittent)

Surface Preparation

Steel Surface

Surface to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000

It is always recommended to apply suitable primer coat before application of this product. Ensure surfaces to be coated is dried and followed over-coating interval and if required sufficiently roughened by emery paper.

This product can be applied over Hand & Power tool cleaning to St2 & St3.

For damage area rectification contact the Technical team of Shalimar Paints limited

Application Details

Method of Application

Airless spray / Brush / Roller

Notes on Airless Spray

Tip Range	21 – 29 thou.
Total Output	2500 – 3500 psi.
Fluid Pressure	(176 - 246 kg/sq.cm.)
Pot Life	3-4 hours
Thinner	Thinner 6756

For Air Spray please contact the Technical team of Shalimar Paints Limited.

Uses

Recommended as intermediate in moderate corrosive area and in Fertilizer Plants, Power & Gas Plants, Refineries, Offshore Structures Bridges and Cranes, Ore Handling Projects, Mining & Machinery Units.

Typical System Selection Guide

SURFACE	1 ST COAT	2 ND COAT	3 RD COAT	4 TH COAT
Steel	Epigard Zinc Rich / Epigard Zinc Phosphate Primer	EPIGARD MIO INTERMEDIATE	Epigard Finish	Epigard Finish / Epigard XL HB Finish
- Do -	-do-	EPIGARD MIO INTERMEDIATE	Epigard XL HB	Shalithane Finish

Chemical Resistance Guide (with suitable top coat)

EXPOSURE	Acids	Alkalis	Solvents	Salt	Water
SPLASH & SPILLAGE	Fair	Good	Very Good	Good	Excellent
FUMES & OUTDOOR EXPOSURE	Fair	Very Good	Very Good	Good	Excellent

Health & Safety

Use Proper Personal Protective Equipment(PPE) during application of this product.

Please consult Material Safety Datasheet (MSDS)

Precaution

Provide adequate ventilation during application and drying. Clean Spray gun equipment and hose immediately after application of material.

Standard Pack Size

20 litres - For available pack size contact local representative of Shalimar Paints Limited

NOTES:

1. This Product datasheet supersedes all previous datasheet and subject to change without prior notice
2. Do not apply when surface temperature is less than 3 °C than dew point.
3. Mixing with mechanical agitator is strongly recommended
4. Use material within stipulated pot life
5. Do not apply paints when environment temperature rises above 50 °C or when relative humidity rises above 85%. Do not apply during rain, fog or mist.
6. Use of thinners other than supplied or approved by Shalimar may adversely affect product performance
7. Drying is dependent on temperature, relative humidity and thickness; ranges is given for considering those parameters
8. System Guide is a typical and for indicative purpose only, however this can have wide range of combination. For details, please contact Shalimar Paints limited
9. Request for details information of surface preparation, paint application on the recommended coating system

DISCLAIMER: This PDS is by no means a comprehensive data. The company will not be liable for losses or damages howsoever caused including liability for negligence, which may be suffered by the user of the data contained therein. It is the user's responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of result is extended since conditions of use are beyond our control. Liability is limited to replacement of the product hence cost of labour charges or consequential damages are excluded.