



**SHALIMAR  
PAINTS**

# MARINE GUARD

## PROTECTIVE COATINGS

### MARINE GUARD 163

Data Sheet No. SPL/PMG/MAR2020004

A two pack low VOC high build mastic surface tolerant epoxy coating reinforced with chemically inert pigment for application on manually cleaned steel surface for enhanced durability and corrosion resistance of steel structures in all corrosive environment including splash zone areas of offshore structures. This is suitable for maintenance coating as dry cargo holds, hulls and decks with excellent overcoating with aged coating .

### Product Information

<b>Color</b>	Grey
<b>Finish</b>	Matt to satin
<b>Flash Point</b>	Above 23°C
<b>Mixing Ratio (By Volume)</b>	Base : Accelerator 3 : 1
<b>Volume Solids</b>	83 ± 2%
<b>Recommended dry film thickness</b>	100-150 microns
<b>Corresponding wet film thickness</b>	121-181 microns
<b>Theoretical Spreading Rate</b>	8.30-5.53 Sq.m/ltr per coat
<b>Drying time</b>	Touch dry      4 - 6    hours Hand dry       18 - 24   hours Full cure        7        days
<b>Interval before Over-coating</b>	Minimum      18    hours Maximum       Indefinite
<b>VOC</b>	170 gm/ltr (EPA Method 24)
<b>Storage Life</b>	Up to 12 months so long as the material is stored in sealed containers under standard warehouse storage condition.
<b>Dry Heat Resistance</b>	Up to 150°C (Intermittent)

### Surface Preparation

#### Steel Surface

Surface to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

It is always recommended to apply suitable primer coat before application of this product. Ensure surface to be coated is dried and followed over-coating interval and if required sufficiently roughened by emery paper.

This product can be applied after Hand & Power tool cleaning to St2 & St3.

*For damage area rectification contact the Technical team of Shalimar Paints limited*

### Application Details

#### Method of Application

Conventional / Airless Spray.  
Brush and roller for touch up painting

#### Notes on Airless Spray

Tip Range	Automatic - 21 - 26 thou. Manual - 15 - 21 thou.
-----------	---

Total Output	1500 - 2500 psi.
Fluid Pressure	(106 - 176 kg/sq.cm.)
Pot Life	2-4 hours
Thinner	Thinner 6756

### Uses

Refineries, Petro chemicals, Fertilizer Plants, Power and Gas Plants, Marine Installations, offshore splash zone Structures, Bridges, Cranes , jetties & sluice gates etc.

## System Selection Guide

SURFACE	1 <sup>ST</sup> COAT	2 <sup>ND</sup> COAT	3 <sup>RD</sup> COAT
- Steel -	MARINE GUARD 163	MARINE GUARD 125	EPIGARD MARINE FINSH

## Chemical Resistance Guide (with suitable top coat)

EXPOSURE	Acids	Alkalis	Solvents	Salt	Water
SPLASH & SPILLAGE	Good	Good	Excellent	Excellent	Excellent
FUMES & OUTDOOR EXPOSURE	Good	Good	Excellent	Excellent	Excellent

## Health & Safety

Please refer to the separate data sheet available with detailed information.

## Precaution

Provide adequate ventilation during application and drying. For proper curing of film, ambient temperature should not be lower than 10° C.

## Standard Pack Size

4 & 20 litres - For available pack size contact local representative of Shalimar Paints Limited

### NOTES:

1. This Product datasheet supersedes all previous datasheet and subject to change without prior notice
2. Do not apply when surface temperature is less than 3 °C than dew point.
3. Mixing with mechanical agitator is strongly recommended
4. Use material within stipulated pot life
5. Do not apply paints when environment temperature rises above 50 °C or when relative humidity rises above 85%. Do not apply during rain, fog or mist.
6. Use of thinners other than supplied or approved by Shalimar may adversely affect product performance
7. Drying is dependent on temperature, relative humidity and thickness; ranges is given for considering those parameters
8. System Guide is a typical and for indicative purpose only, however this can have wide range of combination. For details, please contact Shalimar Paints limited
9. Request for details information of surface preparation, paint application on the recommended coating system

**DISCLAIMER:** This PDS is by no means a comprehensive data. The company will not be liable for losses or damages howsoever caused including liability for negligence, which may be suffered by the user of the data contained therein. It is the user's responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of result is extended since conditions of use are beyond our control. Liability is limited to replacement of the product hence cost of labour charges or consequential damages are excluded.